

PRODUCT DESCRIPTION

A single component, rapid drying modified alkyd primer/finish, designed to provide both anti-corrosive properties and a decorative finish in a single coat.

INTENDED USES

Interlac 789 has been designed for use as a single system to afford anti-corrosive protection for structural steelwork exposed to the environment where cosmetic appearance is important, e.g. in dry internal areas or low corrosivity external environments.

It is particularly suited for use as a rapid drying versatile primer/finish designed to maximize the steel throughput in fabrication yards.

PRACTICAL INFORMATION FOR INTERLAC 789

Color	Available in a wide range via the Chromascan system
Gloss Level	Eggshell
Volume Solids	63%± 3% (depends on color)
Typical Thickness	4 mils (100 microns) dry equivalent to 6.4 mils (159 microns) wet
Theoretical Coverage	253 sq.ft/US gallon at 4 mils d.f.t and stated volume solids 6.30 m ² /liter at 100 microns d.f.t and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless Spray, Air Spray, Brush, Roller

Drying Time

Temperature	Touch Dry	Hard Dry	Overcoating Interval with recommended topcoats	
			Minimum	Maximum
50°F (10°C)	115 minutes	5 hours	6 hours ¹	Extended ²
59°F (15°C)	105 minutes	4.5 hours	5 hours ¹	Extended ²
77°F (25°C)	80 minutes	4 hours	4 hours ¹	Extended ²
104°F (40°C)	60 minutes	3 hours	2 hours ¹	Extended ²

¹ Minimum overcoating times refer to use of recommended topcoats, and may be increased if other topcoats are applied. See Product Characteristics and System Compatibility for further information.

² See International Protective Coatings Definitions & Abbreviations

REGULATORY DATA

Flash Point	31°C (88°F)	
Product Weight	13.1 lb/gal (1.57 kg/l)	
VOC	2.50 lb/gal (300 g/l) 202 g/kg	EPA Method 24 EU Solvent Emissions Directive (Council Directive 1999/13/EC)

See Product Characteristics section for further details

SURFACE PREPARATION

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast clean to SSPC SP6 or Sa2½ (ISO 8501-1:2007). If oxidation has occurred between blasting and application of Interlac 789 the surface should be reblasted to the specified visual standard.

Surface defects revealed by the blast cleaning process should be ground, filled, or treated in the appropriate manner.

Interlac 789 is suitable for application to blast cleaned surfaces which were initially to the above standard but have been allowed to deteriorate under good shop conditions for up to 7-10 days. The surface may deteriorate to Sa2 standard but must be free from loose powdery deposits.

APPLICATION

Mixing	This material is a one component coating and should always be mixed thoroughly with a power agitator before application.		
Mix Ratio	Not applicable.		
Airless Spray	Recommended	Tip Range 17-21 thou (0.43-0.53 mm) Total output fluid pressure at spray tip not less than 2204 psi (155 kg/cm ²)	
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E
Brush	Suitable - Small touch-up areas only	Typically 2.0 mils (50 microns) can be achieved	
Roller	Suitable - Small touch-up areas only	Typically 2.0 mils (50 microns) can be achieved	
Thinner	International GTA007	Do not thin more than allowed by local environmental legislation	
Cleaner	International GTA007		
Work Stoppages	Thoroughly flush all equipment with International GTA007. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or a viscosity increase of the material after storage. Material should be filtered prior to use.		
Clean Up	Clean all equipment immediately after use with International GTA007. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.		
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.		

**PRODUCT
CHARACTERISTICS**

Interlac 789 is designed primarily for the protection of structural steelwork. Alkyd based anti-corrosive products are most suitable for the protection of steelwork in internal dry environments or on exposed steelwork which is situated in low corrosivity environments corresponding to ISO 12944 C1, C2 and C3.

Interlac 789 is available in a wide color range, however, it is in the nature of all alkyd topcoats to be subject to a degree of yellowing and chalking and this will result in the loss of gloss and fading of the specified color over a period of time.

As Interlac 789 is designed as a single coat primer/finish, it is not normally applied as a multiple coat system, other than for repair of mechanical damages, touch-up etc. The minimum overcoating times refer to overcoating Interlac 789 with approved alkyd or oil based topcoats listed below. The use of alternative topcoats can result in increased minimum overcoating times and should be avoided.

Excessive film thickness and/or over-application of Interlac 789 will increase the time to handle, and lengthen drying and overcoating times.

The premature exposure of Interlac 789 to ponding water will cause a color change which may be permanent. This is a cosmetic affect and will not affect the anti-corrosive protection offered by Interlac 789.

Interlac 789 is not designed for exposure in alkaline or acidic environments.

Interlac 789 should not be used in immersed environments.

Note: VOC values are typical and are provided for guidance purpose only. These may be subject to variation depending on factors such as differences in color and normal manufacturing tolerances.

**SYSTEMS
COMPATIBILITY**

Interlac 789 is normally applied as a single coat anti-corrosive primer/finish. Application of a further cosmetic topcoat on site is possible.

Recommended topcoats are:

Interlac 645
Interlac 658
Interlac 665

For further advice on system compatibility contact International Protective Coatings.

**ADDITIONAL
INFORMATION**

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following documents available at www.international-pc.com:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

**SAFETY
PRECAUTIONS**

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

PACK SIZE	Unit Size	Vol	Pack
	20 liter	20 liter	20 liter
	5 liter	5 liter	5 liter
For availability of other pack sizes contact International Protective Coatings			
SHIPPING WEIGHT	Unit Size		
	20 liter		33.1 kg
	5 liter		8.3 kg
STORAGE	Shelf Life	18 months minimum at 77°F (25°C). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	


Disclaimer

The information in this data sheet is not intended to be exhaustive; any person using the product for any purpose other than that specifically recommended in this data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at their own risk. All advice given or statements made about the product (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability at all for the performance of the product or for (subject to the maximum extent permitted by law) any loss or damage arising out of the use of the product. We hereby disclaim any warranties or representations, express or implied, by operation of law or otherwise, including, without limitation, any implied warranty of merchantability or fitness for a particular purpose. All products supplied and technical advice given are subject to our Conditions of Sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is liable to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to check with their local International Paint representative that this data sheet is current prior to using the product.

This Technical Data Sheet is available on our website at www.international-marine.com or www.international-pc.com, and should be the same as this document. Should there be any discrepancies between this document and the version of the Technical Data Sheet that appears on the website, then the version on the website will take precedence.

Issue date: 10/5/2009

Copyright © AkzoNobel, 10/5/2009.

 Copyright © AkzoNobel, 10/5/2009.

www.international-pc.com